

भारत का राजपत्र **The Gazette of India**

प्रसाधारण

EXTRAORDINARY

भाग II—खण्ड 3—उपखण्ड (ii)

PART II—Section 3—Sub-section (ii)

प्रति कार से प्रकाशित

PUBLISHED BY AUTHORITY

सं० 396]

नई दिल्ली, शक्रवार, अगस्त 11, 1967/श्रावण 20, 1889

No. 396]

NEW DELHI, FRIDAY, AUGUST 11, 1967/SRAVANA 20, 1889

स भाग म भिन्न पृष्ठ संख्या दी जाती है जिससे कि यह अलग संकलन के रूप में रखा जा सके

Separate paging is given to this Part in order that it may be filed as a separate compilation.

MINISTRY OF COMMERCE **NOTIFICATIONS**

New Delhi, the 11th August 1967

S.O. 2779.—In exercise of the powers conferred by section 6 of the Export (Quality Control and Inspection) Act, 1963 (22 of 1963), and in continuation of the notification of the Government of India, in the Ministry of Commerce S. O. 3918 dated the 16th December, 1965, and after previous publication as required by sub-rule (2) of rule 11 of the Export (Quality Control and Inspection) Rules, 1964 and after consulting the Export Inspection Council, the Central Government being of opinion that it is necessary and expedient so to do for the development of the export trade of India, hereby:—

- (1) notifies that the additional items of coir products specified in Annexure I to this notification shall be subject to quality control and inspection prior to export;
- (2) specifies the inspection in accordance with the Export of Coir Products (Inspection) Rules, 1965, as the type of inspection which will be applied to the said coir products prior to their export;
- (3) recognises—
 - (a) the specifications for each item of the Coir products specified in Annexure I shall be as set out respectively in Annexure II, III and IV to this notification,
 - (b) the specifications as declared by the exporter to be the agreed specifications of the export contract provided they fall in between the range of the minimum of the specifications for that quality and the next higher recognised under clause (a), and

(1341)

- (c) the specifications other than those recognised under clauses (a) and (b), but are formulated by a panel of experts appointed by the Coir Board for the purpose of examining and approving samples submitted by the exporter;
- (4) prohibits the export in the course of international trade of any of the said coir products unless the same is accompanied by a certificate issued by the Chairman Coir Board or an officer of the Board authorised by the Chairman in this behalf to the effect that the aforesaid coir products conform to any one of the specifications recognised under sub-paragraph (3).
2. Nothing in this notification shall apply to the export by sea, land or air, of samples of these aforesaid coir products to prospective buyers.
3. This notification shall come into force on the 18th September, 1967.

ANNEXURE I

Coir mats

- (a) Gymnasia
- (b) Sinnet
- (c) Corridor

ANNEXURE II

Specifications for Coir Mats for Gymnasia

1. General Requirements—

1.1. Mats shall be manufactured from yarn specified in the Table below and shall be firmly and evenly woven. The pile tufts shall be secure and the cropping of the pile shall be uniform and of one level.

1.1.1. Each mat shall be bound with a braid closely plaited with 11 strands of clean, hard-twisted yarn and having a width of 30 mm and the ends of the braid shall be securely fastened. The cordage if used shall consist of either coir or hemp rope made from hard-twisted yarn and having a circumference of 38 mm or 11 ply braid of 25 to 30 mm width made from clean, hard-twisted yarn.

2. Specific Requirements—

2.1. *Construction*—The two qualities of mats shall conform to the requirements given for each in the said Table.

NOTE.—The quality numbers in the said Table are the code names reserved by the Coir Board.

2.2. *Pile Height*—The pile height of the finished mats shall be 63 mm. A tolerance of 3 mm shall be permitted.

2.3. *Dimensions*—The dimensions of the mats shall be as agreed to between the buyer and the seller. Unless specifically agreed otherwise, a tolerance of 13 mm in the dimensions shall be permitted.

2.4. *Weight*—The weight per square metre (or square foot) of the two qualities of mats shall be within the ranges given for each in the said Table.

3. Packing—

3.1. The mats shall be suitably packed, care being taken to see that the pile of the mats is not crushed while packing.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name, initials, trade-mark, or any other identification mark of the exporter.

THE TABLE
Constructional Details for Coir Mats for Gymahasia
 (Sub-clause 1·1 of clause 1, sub-clause 2·1 and 2·4 of clause 2)

Quality Number	Pile-yarn	Wcft	Warp	Pile height	Weight Kg/M ² (or oz/ft ²)
1	2	3	4	5	6
BVGI	VYCOME Yarn unbleached and free from impurities and pith, 4 toppings, that is minimum four fold yarn drawn together.	VYCOME Yarn Single, Sufficient to guarantee tight weave.	VYCOME Yarn 10 ends per decimetre.	63 mm.	11·6 to 12·8 (or 38 to 42)
BBGI	BEACH Yarn bleached or unbleached, 3 toppings or minimum three-fold Yarn drawn together.	BEACH Yarn single, sufficient to guarantee tight weave.	VYCOME Yarn 10 ends per decimetre.	63 mm.	10·4 to 11·6 (or 34 to 38)

ANNEXURE III

Specification for Corridor Mat

1. General Requirements—

1.1. The mats shall be manufactured from plain or dyed coir-yarn braid and shall be stiched in such designs or patterns as may be specified by the buyer.

2. Specific Requirements—

2.1. The constructional details of the mats of the quality numbers listed in the table shall be as specified against each in the Table below.

NOTE—The quality numbers in the said table are the Code names reserved by the Coir Board.

2.2. *Dimensions*—The dimensions of the mats shall be as agreed to between the buyer and the seller. Unless specifically agreed to otherwise a tolerance of +13 mm in the dimensions shall be permitted.

2.3. *Weight*—The weight per square metre (or square foot) of the mats of the quality numbers listed in the said Table shall be in accordance with the relevant requirements in the said Table. A tolerance of +5 per cent on the weight shall be permitted.

3. Packing—

3.1. The mats shall be packed as agreed to between the buyer and the seller.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name, initials, trade-mark, or any other identification mark of the exporter.

THE TABLE
Constructional Details of Sinnet Mats
 (Sub-clauses 2.1 and 2.3 of Clause 2)

Quality Number	Material		Braid		Weight		
	Quality of Yarn	Scoreage Min.	No. of strands of ply	Thickness mm. in.	Kg/m ² oz/ft ²		
1	2	3	4	5	6	7	8
SA1	Anjengo	12	9	19	0.75	3.65	12
SA2	"	12	9	19	0.75	4.25	14
SA3	"	12	11	25	1.00	4.85	16
SA4	"	12	11	25	1.00	5.45	18
SA5	"	12	11	25	1.00	6.10	20
SR1	Aratory	12	9	19	0.75	3.35	11
SR2	"	12	9	19	0.75	3.95	13
SR3	"	12	11	25	1.00	4.60	15
SR4	"	12	11	25	1.00	5.20	17
SR5	"	12	11	25	1.00	5.80	19
SV1	Vycome	11	9	19	0.75	3.65	12
SV2	"	11	9	19	0.75	4.25	14
SV3	"	11	11	25	1.00	4.85	16
SV4	"	11	11	25	1.00	5.45	18
SB1	Beach	..	9	19	0.75	3.35	11
SB2	"	..	9	19	0.75	3.95	13
SB3	"	..	11	25	1.00	4.60	15

NOTE.—Coir yarn for the inner strands of the braid may be of a suitable quality.

ANNEXURE IV *Specifications for Corridor Mats*

1. General Requirements—

1.1. The mats shall be firmly and evenly woven.

1.1.1. The mats may be supplied plain or dyed or with simple designs as may be specified by the buyer.

1.1.2. The mats shall be free from extraneous matter and salt.

2. Specific Requirements—

2.1. *Construction*—The mats shall conform to the constructional details given in the Table below.

2.2. *Dimensions*—The Dimensions of the mats shall be as agreed to between the buyer and the seller. Unless specifically agreed otherwise, a plus tolerance of 2 per cent subject to a maximum of 19 mm and a minus tolerance of 2 per cent subject to a maximum of 13 mm in dimensions shall be permissible.

2.3. *Ends*—The minimum number of ends per decimetre (or foot) of the mats listed in the said Table shall be in accordance with the requirements indicated in that Table against each.

2.4. *Weight*—The weight per square metre (or square foot) of corridor mats shall be as specified in the said Table. A tolerance of ± 5 per cent on the weight so specified shall be permitted.

3. Packing—

3.1. The mats shall be packed as agreed to between the buyer and the seller.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name initials trade-mark, or any other identification mark of the exporter.

THE TABLE
Constructional Details of Corridor Mat.
(Sub-clauses 2.1, 2.3 and 2.4 of clause 2)

Quality Number	Warp		Weft		Weight
	Quality of yarn	Ends per dm (or per foot) Min.	Quality of yarn	Scorage Min.	Kg/ m ² (or oz/ft ²)
1	2	3	4	5	6
AC1	Rope yarn	6(or 18/19)	Angengo	13	4·55(or 15)
AC2	"	5(or 14/15)	"	13	4·25(or 14)
AC3	"	5(or 14/15)	"	12	3·65(or 12)
RC1	"	6(or 18/19)	Aratory	13	4·25 (or 14)
RC2	"	5(or 14/15)	"	13	4·00(or 13)
RC3	"	5(or 14/15)	"	12	3·35(or 11)
LC1	"	5(or 14/15)	Alapat	12	4·25(or 14)
WC1	"	5(or 14/15)	Vycome	13	4·25 (or 14)
WC2	"	5(or 14/15)	"	12	3·65(or 12)
WC3	"	5(or 14/15)	"	11	3·05(or 10)
TC1	"	5(or 14/15)	T. VYcome	..	3·65(or 12)
TC1	"	5(or 14/15)	Beach	..	3·05(or 10)

[No. 60(9) Exp. Insp/67.]

S.O. 2780.—In exercise of the powers conferred by section 17 of the Export (Quality Control and Inspection) Act, 1963 (22 of 1963), the Central Government hereby makes the following rules further to amend the Export of Coir Products (Inspection) Rules, 1965, namely:—

1. These rules may be called the Export of Coir Products (Inspection) Second Amendment Rules, 1967.

2. In the Export of Coir Products (Inspection) Rules, 1965, for rule 2, the following rule shall be substituted, namely:—

"2. *Definition*—In these rules, "Coir Products" mean (i) coir door mats, and (ii) coir mats, of the following types, namely:—

(1) *Coir door mats*

- (a) Creel
- (b) Bit
- (c) Fibre
- (d) Rod

(11) *Coir mats*

- (a) Gymansia
- (b) Sinnet
- (c) Corridor."

[No. 60(9) Exp. Insp/67.]

A. C. BANERJEE, Jt. Secy.

